

EN ISO 20345:2022

Class: S3S FO SC SR ESD Sizes: 34-48 Available in stock only sizes 38-48 Instep: 12 Weight (±10%): **620 gr**. ^(*)

Description: high shoe in black nubuck leather, water-repellent with padded storm-cuff; HIGH-TEX inserts, 100% polyester lining, non-metallic HRP Insole, ATOMIC insole, anatomic, antistatic, breathable and ESD, translucid double density polyurethane with overcap, bending resistant, abrasion resistant, oil resistant, slip resistant, ESD

TECHNICAL SHEET ART. FIREBRAND

Plus: midsole compound particularly studied to get a soft PU density for a higher comfort **Suggested sectors of usage:** Farming / Zootechnics, Building / Construction, Mechanical industry, Naval Industry, Servicing, Professional / Craftsman

Care and Maintenance: clean periodically the outsole and the upper with non-aggressive substances which could compromise quality, safety and durability of the shoe, do not dry close to direct heat source



Complete shoe	Norm	Description	Unit	Results	EN ISO 20345 requirements
Toe Cap : non-metallic toe cap TOP COMPOSITE, impact resistant 200 J	5.3.2.6	Impact resistance	mm	15	≥ 14
	5.3.2.7	Compression resistance	mm	15	≥ 14
Midsole: non-metallic HRP Insole with high tenacity fibres multi layers, polyester composition, perforation resistant	6.2.1	Perforation resistance (single value)	Ν	1408	≥ 950
		Average value		1467	≥ 1.100
ESD footwear: dissipation capacity of the electrostatic charge	EN ISO 61340-5-1	Electrical resistance for ESD footwear	Mohm	2,01	< 100
Capacity of Energy Absorption in the heel area	6.2.4	Energy absorption in the heel area	J	28	≥ 20
Upper : black SAFETY-NUBUCK, with padded storm-cuff. HIGH-TEX inserts	5.4.3	Tear strength	Ν	133	≥ 60
	5.4.6	Water vapour permeability	mg/cm² · h	4,8	≥ 0,8
		Water vapour coefficient	mg/cm ²	40,3	≥ 15
Vamp/Quarter Lining : honeycomb 100% finished polyester, breathable, abrasion resistant, blue colour	5.5.4	Water vapour permeability	mg/cm² · h	24,6	≥ 2
		Water vapour coefficient	mg/cm ²	198,8	≥ 20
	5.5.2	Tear strength	Ν	28	≥ 15
	5.5.3	Abrasion resistance (dry)	cycles	no holes	25.600
		Abrasion resistance (wet)	cycles	no holes	12.800
Sole: double density polyurethane, bending resistant, abrasion resistant, oil	5.8.3	Tear strength	kN/m	15	≥ 8
resistant, slip resistant, ESD	5.8.4	Abrasion resistance (black)	mm ³	67	≤ 150
	5.8.5	Bending resistance	mm	0,5	≤ 4
	5.8.6	Hydrolysis	mm	0,7	≤ 6
	6.4.2	Hydrocarbons resistance (volume increase)	%	6,8	≤ 12%
	6.2.10	Slip resistance on ceramic floor with water	heel forward (7°)	0,46	≥ 0,31
		and detergent	tip back (7°)	0,47	≥ 0,36
		Slip resistance on ceramic glycerine (SR)	heel forward (7°)	0,25	≥ 0,19
			tip back (7°)	0,27	≥ 0,22